
TECHNICAL DATA SHEET
(Additive MFQ-STEА-CA)

• **Product Description:**

MFQ-STEА-CA as most environmental friendly PVC heat stabilizers, it has very good process performances.
MFQ-STEА-CA good thermal stability & weather ability.
MFQ-STEА-CA anti-severe sunlight, anti-sulfide pollution.
MFQ-STEА-CA good compatibility & dispersion with PVC.
MFQ-STEА-CA its economic property in soft/semi-rigid applications.

• **General Properties:**

Forms	•Very fine powder
Color	•White

• **Technical Specifications:**

Moisture: Max	3	%
Free fatty acid	1.00	%
Melting point	150 – 160	°C
Ash content	9.2– 10.2	%
Density	1.08	gr/cm ³
Sieve residue at 500 mesh	≤ 1	%
phr	3-5	

ATTENTION

- ✓ **Dosage:** 3% to 5% film depending on final application and thickness.
- ✓ **Lifetime and Storage:** Not to exceed 12-18 months. Keep in cool and dry place under shelter for long periods.

* This product packed in PP Woven bag of 25 kg each

+98-21-77850536

www.marinafq.com